

## Sleek HS Melamine Topcoat

### PRODUCT DESCRIPTION

Indigo Sleek HS Melamine system comprising of Sealer & Topcoat is a quick drying two pack system designed for the protection and beautification of interior furniture & joinery.



### PERFORMANCE FEATURES & BENEFITS

- Quick drying
- High-solid formulation for better filling of wood grains
- Extra durable

### FINISH

**MATT**

**GLOSS**

SILK MATT

### MIXING RATIO

9:1 by volume  
(9 parts of base : 1 part of hardener)

### RECOMMENDED USES

#### AREA



INTERIOR



EXTERIOR

#### SURFACES

It can be used on all types of interior wood like doors, windows, furniture, kitchen cabinets etc.

### APPLICATION DETAILS & SURFACE PREPARATION

#### MIXING



Shake well before use

#### TOOLS



Brush, Spray

#### THINNING



\* For Brush application:  
Sleek Melamine Brushing Thinner  
For Spray application:  
Sleek Melamine Spraying Thinner

#### THINNING RATIO

Sleek Melamine Thinner -  
Brushing -20 -30 %  
Sleek Melamine Thinner -  
Spraying -30-40 %

#### SURFACE DRYING TIME



10-15 minutes at 30°C

#### FILLING



Sleek HS Melamine Sealer

#### APPLICATION ENVIRONMENT



Temperature:  
10-40 Degree  
Humidity: Below 80%

#### CLEANING



Ensure that the wood is seasoned and the surface is well-dried.

- To remove the oiliness inherent to tannin rich wood such as teak and rose wood, wipe clean with NC thinner.

#### SURFACE PREPARATION



- Sand the wooden substrate along the grains, sequentially, with abrasive paper from grit numbers 80 to 180.
- The dust, dirt that comes out during the sanding process should be totally removed.
- Apply 2-3 coats of Sleek HS Melamine Sealer depending on the filling required.
- Drying time between coats 3-4 hours & inter-coat sanding using abrasive paper grit number 320.

#### APPLICATION



Apply 2 coats of Sleek HS Melamine Topcoat by brush / spray with 4-6 hours drying time between coats. Intercoat sanding using abrasive paper grit number 400

#### SAFETY FEATURES



No added Lead, Mercury or Chromium compounds

## TECHNICAL DATA

Coverage	6 - 7 sqm/L/Coat
Drying Time	4-5 hours
Sheen level	90-95° - Glossy 10-15° - Matt
Flash point	Above 23°C.
Stability of thinned paint	8 to 10 hours pot life
Appearance	Clear
Solids	62+/-1%
Specific gravity	1
Recommended DFT	30 to 35 microns per coat
Viscosity @25°C by Stormer Viscometer	-
Pot life	8-10 hours after base & hardener are mixed at 30°C
Shelf life	12 months
Contrast ratio	NA

*\*Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application as well as surface roughness.*

## PRECAUTIONS

- Flammable
- Keep away from heat, sparks etc.
- Use appropriate protection during application.
- Ensure adequate ventilation during application.

## POST APPLICATION INSTRUCTIONS

-

## AVAILABLE PACK SIZE

Available in:



500 ml



1 L



4 L



10 L



20 L

## SHADE RANGE

NA



INDIGO

Be surprised!